



PRO COAT WASHABLE INTERIOR

Production Description

Premium quality, 100% pure acrylic based Ultra Low Sheen finish for interior coating purposes. It possess superior coverage on concrete, brick, fibre-cement board, masonry, etc. The product is easy to apply, has excellent coverage and low dirt pickup.
Superior Mould Resistance and 10 Year Guarantee***

*** Conditions apply, refer to guarantee terms and conditions.

Areas of Application

Timber, weatherboards, concrete, plaster, concrete blocks, brickwork, cement render, wallboard PVC and cement sheets. Wallboard, Weatherboards, Concrete, Plaster, Concrete blocks, Brickwork, Cement render, Timber, PVC & Cement sheets. Designed for interior use in areas prone to high wear.

Technical Data

Colour Range	White & Tint bases.
Gloss Level at 60° head	0% - 3%
Solvent Resistance	Being thermoplastic film sensitive towards alcohol & aromatic hydrocarbons
Toxicity	Dry film is not toxic
Thinning & Clean Up	Water
Thinning Rate	Up to 5% thinner may be necessary depending on method of application and climatic conditions.
Theoretical Coverage**	10-12 sq. m. / litre per coat. Practical coverage may depend on surface profile, method of application and losses.
Drying Time (at 25°C & RH 60%)*	Touch dry: 30 minutes* / Recoat: 4 - 6 hours*
Packs available	1 litre, 4 litre, 10 litre, 15 litre. 20 litre

*Cooler temperature, higher film thickness and higher humidity conditions will require longer drying times

**Practical coverage may depend on surface profile, method of application and losses. Higher film thickness will lead to lower coverage.

Method of Application

Brush, Roller or Spray. Please use the method best suited to your requirement and skill. The use of a synthetic sleeve of 8 mm nap on a smooth surface is recommended. For airless Spray application, optimum pressure of 2800 psi and nozzle size of 0.013-0.015 inches is suggested as a guideline.

Surface Preparation

Remove dust, dirt, and grease from the surface to be painted. If mould or fungus is present on the surface, wash it with a commercially available bleaching agent and then treat with antifungal solution. Fill cracks with suitable proprietary filler and sand smooth using 180 - grit sandpaper. Light sanding using 220 - grit sandpaper must be carried out on smooth surfaces after the application of sealers or undercoats to prepare an even substrate. Previously unpainted cement, concrete or bricks will need to be cleaned with a stiff

Australian Paint Company Pty Ltd

SYDNEY

13-27 Melbourne Road, Riverstone NSW 2765
P: (02) 9832 0000

BRISBANE

444 Newman Road, Geebung QLD 4034
P: (07) 3265 7890

E: info@apccoatings.com.au
www.apccoatings.com.au



brush. No Primer is needed over concrete and cement (three or more coats may be required depending on how porous the substrate). Allow concrete, masonry and cement surfaces to cure for 28 days or until the alkalinity drops below PH10 before coating. Remove loose sand with a broom to provide a sound surface for painting.

PRO COAT WASHABLE INTERIOR

Application

Stir the contents thoroughly before & during use. Apply uniformly direct from the container after proper surface preparation and suitable priming. Two coats of Luxe Interior Ultra Low Sheen are normally recommended. Certain bright colours may require a third coat to ensure proper colour uniformity. On old galvanised surfaces and roofs apply one coat of Omega RustBlock Heavy Duty Primer after cleaning, followed by two finishing coats. Use Omega RustBlock Etch Primer on new galvanised iron surfaces. When applying on old powder coated roofs, clean the surface first. Sand the surface lightly to provide mechanical key to the paint film. If there is any spot rust, prepare and touch it up with Omega RustBlock Heavy Duty Primer. Bare and unpainted timber high in tanning stain will require an oil based undercoat/primer prior to application of finishing coats.

Mix and Colour Check

Mix the paint before application with a wide flat (25mm) paddle or a hand paint mixer with a perforated base, in a circular lifting motion from the bottom of the container for 5 minutes or until the paint and colour are thoroughly mixed. Remix the paint every 2 hours to ensure product consistency. Check the colour chart prior to application. Inner mix multiple containers together to ensure colour consistency. Replace and secure container lid during painting to prevent the paint drying within the container.

Coating Maintenance

Washing the painted surface periodically will maintain the look of a newly painted surface longer. Clean the surface with a diluted sugar soap or a mild detergent and rinse well with clean water. Do not use scouring pads, abrasive brushes, high pressure washing or solvent to clean the painted surface. These will damage the paint film and cause premature failure of the coating.

Flammability & Transport Information

- Non-flammable.
- Ensure container is upright with lid secure.
- Ensure the container is secured in the vehicle for transport.

Environmental

- Do not wash painting equipment and allow waste to enter drains and waterways.

Australian Paint Company Pty Ltd

SYDNEY

13-27 Melbourne Road, Riverstone NSW 2765
P: (02) 9832 0000

BRISBANE

444 Newman Road, Geebung QLD 4034
P: (07) 3265 7890

E: info@apccoatings.com.au
www.apccoatings.com.au



**AUSTRALIAN
PAINT COMPANY** **PRO
SERIES**



The technical information and suggestions for use and application are given in good faith. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise. The manufacturer does not assume any liability for any loss or injury resulting from the use of the product. Cooler temperature, higher film thickness and higher humidity conditions will require longer drying times.

Safety & Precautions

- Do not apply when surface temperature is below 10°C or over 35°C.
- Do not apply in environments of high humidity/moisture, or if pending rain is a possibility.
- Use only the recommended thinner for dilution and cleaning.
- Check paint colour to the colour chart/standard prior to application.
- Provide adequate ventilation during use.
- Keep out of reach of children.
- Avoid exposure of the new paint film to steam for 48 hours and to washing or scrubbing for 7 days.
- Check cross cut adhesion test of old coating before repainting.
- Apply a test sample for compatibility of this product over a small test area.
- Always refer to SDS first prior to commencement of painting jobs.
- Do not dispose of unwanted paint and thinners that will enter drains and water ways.
- Refer to state / local EPA and council web sites for environmental and safe disposal details.

APCO Coatings 13-27 Melbourne Road Riverstone NSW 2765 Phone (02) 9832 0000 /
info@apccoatings.com.au
Reviewed June 2019

Australian Paint Company Pty Ltd

SYDNEY

13-27 Melbourne Road, Riverstone NSW 2765
P: (02) 9832 0000

BRISBANE

444 Newman Road, Geebung QLD 4034
P: (07) 3265 7890

E: info@apccoatings.com.au
www.apccoatings.com.au