

322 Chassis Black Enamel

Production Description

Single pack quick drying enamel based on modified alkyd. It is specially designed enamel for automotive chassis to provide excellent weathering properties. No need to apply primer before application of this product.

Areas of Application

The product is recommended for protection and maintenance of all automotive chassis. Suitable for interior and exterior use.

Technical Data

Colour	Black
Solvent Resistance	Fair
Toxicity	Dry film is nontoxic
Thinning & Clean Up	Omega Enamel Thinner. Up to 10% thinner can be used depending on weather and application method.
Theoretical Coverage*	10 sq.m. / litre at 40 microns DFT. Depends on surface profile*
Drying Time (at 25 C & RH 60%) **	Touch dry in 10-15 minutes / Recoat after 8 hours**
Sheen Level	Satin
Packs available	4 litres and 20 litres

*Practical coverage depends on surface profile, method of application and dry film thickness. Higher film thickness leads to lower coverage.

** Cooler temperature, higher film thickness, or higher humidity conditions will lead to longer drying times.

Method of Application

Can be applied by brush, roller, or spray. Please use the method best suited to your requirement and skill.

Surface Preparation

Ensure that the surface to be painted is free from all contaminants like oil, grease, and wax by wiping with thinner. Sand the surface with emery 180 grit to provide mechanical key for adhesion. While repainting, remove loosely adhered paint and clean the surface.

Application

Stir the contents thoroughly before use. Add recommended thinner if necessary, as per climatic condition and apply uniform coat. Second coat of Chassis Black can be applied after 8 hours drying of first coat. Do not apply at temperature below 10 °C and provide adequate ventilation during use.

Flammability & Transport

- Highly Flammable.
- Keep away from source of ignition.
- Ensure container is upright with lid secure during transit.
- Ensure the container is secured in the vehicle for transport.



Australian Made & Australian Owned



322 Chassis Black Enamel

Environmental

- Do not wash painting equipment and allow waste to enter drains and water ways.
- Do not dispose of unwanted paint and thinners that will enter drains and water ways.
- Refer to state / local EPA and council web sites for environmental and safe disposal details.

Safety & Precautions

- Do not apply when surface temperature is below 10 °C
- Use only the recommended thinner for dilution and cleaning.
- Provide adequate ventilation during use.
- Please refer to the Material Safety Data sheet before using the product.
- Keep out of reach of children
- Check crosscut adhesion test of old coating before recoating.

Disclaimer: In lieu of all warranties expressed or implied, the seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Neither the seller nor manufacturer shall be liable for any injury, loss, damage, direct or consequential, arising out of the use of or inability to use this product. Since the use and application of this product is beyond the control of the seller and the manufacturer, the purchaser and user assume all risk and liability whatsoever, in connection with this product therewith.

Omega Paints Pty Ltd., 13-27 Melbourne Road Riverstone 2765 Phone (02) 9832 0000 /
info@omegapaints.com.au
Reviewed April 2021