



SUREPREP 3-IN-1 ACRYLIC PRIMER/SEALER/UNDERCOAT

Production Description

A premium quality, fast drying, water based, interior and exterior, multipurpose primer/sealer/undercoat. Formulated primarily to provide a sealed and sandable surface for acrylic and solvent based topcoats. Combines the qualities desired in an interior/exterior primer: Excellent adhesion, and filling properties, low spatter, sandability, minimal odour, excellent flow and levelling. May be applied by brush, roller or spray. Contain anti fungicidal additives and may be tinted to facilitate contrasting colours. Complies with APAS Standard APAS 0172 and is environmentally friendly, non-toxic, nonhazardous and non-flammable.

Areas of Application

Wallboard, Plasterboard, interior timber and exterior plaster and concrete. This product is suitable for application on previously painted or unpainted surfaces. If using over plastered surfaces, use this product only after complete curing and cleaning of plaster.
For interior and exterior use.

Technical Data

| | |
|--------------------------------|---|
| Colour Range | White. May be tinted to facilitate pastel colours. |
| Sheen Level | Flat |
| Solvent Resistance | Being thermoplastic film sensitive towards alcohol & aromatic hydrocarbons |
| Toxicity | Dry film is not toxic |
| Thinning & Clean Up | Water |
| Thinning Rate | Up to 5% thinner may be necessary depending on method of application and climatic conditions. |
| Theoretical Coverage** | 14 sq. m. / litre per coat. Practical coverage may depend on surface profile, method of application and losses. |
| Drying Time (at 25C & RH 60%)* | Touch dry: 30 minutes* / Recoat: 2 - 3 hours* |
| Packs available | 4 litre, 10 litre, 15 litre. 20 litre |
| Complies to APAS Standard | APAS 0163/1 |

Method of Application

Brush, Roller or Spray. Please use the method best suited to your requirement and skill. The use of a synthetic sleeve of 10 mm pile on a smooth surface is recommended For airless spray application, optimum pressure of 2700 psi and nozzle size of 0.013-0.015 is suggested as a guideline.

Australian Paint Company Pty Ltd

SYDNEY

13-27 Melbourne Road, Riverstone NSW 2765
P: (02) 9832 0000

BRISBANE

444 Newman Road, Geebung QLD 4034
P: (07) 3265 7890

E: info@apccoatings.com.au
www.omegaint.com.au/pro-series



Surface Preparation

Remove all surface contamination and ensure the surface clean and dry and free of dust, dirt, grease, etc. If mould or fungus is present on the surface, wash with a commercially available bleaching agent and then treat with antifungal solution. For previously painted surfaces, remove all loose and flaking paint. Check cross cut adhesion test of old paint before repainting Sand with 180 - mesh sandpaper to reduce previous film to a flat finish. Wash with sugar soap rinsing thoroughly with clean water. Touch up bare areas with SurePrep Primer Sealer Undercoat and apply to dry before applying a full coat of SurePrep Primer Sealer Undercoat over the entire surface.

SUREPREP 3-IN-1 ACRYLIC PRIMER/SEALER/UNDERCOAT

Application

Stir the contents thoroughly before and during use. Apply one or two uniform coats with light sanding in between using 220- grit sandpaper. Dust off and follow with two finish coats.

Mix and Colour Check

Mix the paint before application with a wide flat (25mm) paddle or a hand paint mixer with a perforated base, in a circular lifting motion from the bottom of the container for 5 minutes or until the paint and colour are thoroughly mixed. Remix the paint every 2 hours to ensure product consistency.

Check colour to the colour chart/standard prior to application. Inner mix multiple containers together to ensure colour consistency. Replace and secure container lid during painting to prevent the paint drying within the container.

Flammability & Transport Information

- Non-flammable.
- Ensure container is upright with lid secure.
- Ensure the container is secured in the vehicle for transport.

Environmental

- Do not wash painting equipment and allow waste to enter drains and water ways.
- Do not dispose of unwanted paint and thinners that will enter drains and water ways.
- Refer to state / local EPA and council web sites for environmental and safe disposal details.

Safety & Precautions

- Do not apply when surface temperature is below 10⁰ C or over 35⁰ C
- Do not apply in environments of high humidity/moisture, or if pending rain is a possibility.
- Apply in calm fine weather conditions and only during daylight hours.
- Cease painting 2 hours before sunset or if weather changes are forecast.
- Use only the recommended thinner for dilution and cleaning.
- Check paint colour to the colour chart/standard prior to application
- Provide adequate ventilation during use.

Australian Paint Company Pty Ltd

SYDNEY

13-27 Melbourne Road, Riverstone NSW 2765
P: (02) 9832 0000

BRISBANE

444 Newman Road, Geebung QLD 4034
P: (07) 3265 7890

E: info@apccoatings.com.au
www.omegaint.com.au/pro-series



**AUSTRALIAN
PAINT COMPANY** **PRO
SERIES**



- Keep out of reach of children
- Avoid exposure of the new paint film to steam for 48 hours and to washin/scrubbing for 7 days.
- Check cross cut adhesion test of old coating before repainting.
- Apply a test sample for compatibility of this product over a small test area.
- Always refer to SDS prior to commencement of application.

The technical information and suggestions for use and application are given in good faith. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise. The manufacturer does not assume any liability for any loss or injury resulting from the use of the product. Cooler temperature, higher film thickness and higher humidity conditions will require longer drying times.

APCO Coatings 13-27 Melbourne Road Riverstone NSW 2765 Phone (02) 9832 0000 /
info@apccoatings.com.au

Reviewed June 2019

Australian Paint Company Pty Ltd

SYDNEY

13-27 Melbourne Road, Riverstone NSW 2765
P: (02) 9832 0000

BRISBANE

444 Newman Road, Geebung QLD 4034
P: (07) 3265 7890

E: info@apccoatings.com.au
www.omegaint.com.au/pro-series